

FLOCEM POLYMER MODIFIED CEMENT BASED FLOOR OVERLAY

FLOCEM is a polymer modified natural aggregates cementitious overlay designed for flooring operation. Its excellent abrasion and mechanical resistance properties (approximately 60 MPa compressive strength) make it suitable for heavy duty industrial. FLOCEM has been formulated for easy application to achieve a smooth, flat surface without any shrinkage and cracking up to 10-20 mm thickness.

FIELD OF APPLICATION

- Reinstatement of damaged/old, new or existing concrete floors subject to foot traffic, industrial equipment, airport, petrochemical, power plant, forklift traffic or trolleys.
- Use as final wearing coarse overlay or may be coated with an appropriate epoxy floor coating.
- Residential, commercial and industrial application
- Light to medium industrial application

ADVANTAGES

- Good flowing properties, eliminates the need for admixtures
- Controlled expansion and non-shrinkage
- Reinstating large areas in relative short time periods
- Rapid hardening
- Dimensionally stable
- Long lasting durable
- Good adhesion to most common substrates
- Can be applied directly onto prepared concrete surfaces
- Single component product, just add water
- Installation can be carried out in a single application
- Very fast application
- Easy mixing

COVERAGE

For every 10 mm thickness 20.0 to 25.0 kg (depend on substrate conditions) of dry powder per square meter will be required.

SUBSTRATE PREPARATION

Ensure the concrete substrate is clean and free from oil, grease, sealers, curing compounds, paints, polymer coatings, dust or other foreign (bond breaking) matter. Excess bitumen, adhesive or laitance should be removed by light scrubbing or mechanical captive shot blasting or grinding, followed by vacuuming to remove debris and dust. The substrates should be pre-saturated for preferably 6 hours with water before application.



موسسه استاندارد و تحقیقات صنعتی ایران
تائیدیه صلاحیت آزمایشگاه همکار



مرکز ملی تایید صلاحیت ایران
ISO / IEC 17025



مجوز صادرات
به اتحادیه اروپا



استاندارد ملی ایران

تهران، خیابان سهروردی شمالی، خیابان شهید قندی غربی، ساختمان شماره ۱۲۴، واحد ۱ | تلفکس: ۸۷۷۵۴

www.abadgarangroup.com

info@abadgarangroup.com

Revision Date: 29/12/2020



واحد تولیدی نمونه ملی

MIXING

FLOCEM requires approximately 2.5 litres of water per 25 kg bag and is best mixed with a forced action, high shear stirrer, or by a heavy duty electric mixing drill at approx. 600 rpm. Add pre measured water to a clean mixing bucket. Gradually add FLOCEM into the water whilst continuously mixing the contents of the bucket.

When the entire contents of the bag have been added to the water, mix for a further two minutes to produce a smooth homogenous consistency. Do NOT mix by hand. Do NOT add excess water. Discard any FLOCEM that has hardened or stiffened in the mixing bucket. Further addition of water will NOT reconstitute a usable mixture.

APPLICATION

The mixed material is poured onto the prepared substrates and spread with a steel trowel and spreader to the required thickness in one operation. Alternatively the use of an electrical trowel will ensure a smooth even finish.

CURING

Start curing after initial setting of FLOCEM, It necessary to cure areas of FLOCEM with humidified method for at least 24 hours.

Protect from direct sunlight or drying winds during cure.

Note: after curing, cutting operation for expansion joint be done.

PHYSICAL AND CHEMICAL PROPERTIES

Physical state: Powder

Color: Grey

Specific gravity of fresh mortar: $2.40 \pm 0.1 \text{ g/cm}^3$

Chloride ion: Nil

Pot life: 20 minutes @ +25°C

STORAGE & SHELF LIFE

Shelf life: 1 year in the original package

Storage condition: should be protected from direct sunlight and moisture. Keep bag in the temperature range between +10°C and +30°C

Packing: 25 kg bag

HEALTH AND SAFETY

This product does not contain any substances hazardous to human health and the environment. However, it should not be swallowed and allowed to be in contact with skin and eyes. In case of contact with eyes, rinse immediately with plenty of water. When applying gloves & goggles should be worn. For further information refer to the material safety data sheet.

FLOCEM is not flammable. MSDS is available at ABADGARAN website.

TECHNICAL SERVICE

موسسه استاندارد و تحقیقات صنعتی ایران
تائیدیه صلاحیت آزمایشگاه همکار



مرکز ملی تائید صلاحیت ایران
ISO / IEC 17025



مجوز صادرات
به اتحادیه اروپا



استاندارد ملی ایران



واحد تولیدی نمونه ملی

تهران، خیابان سهروردی شمالی، خیابان شهید قندی غربی، ساختمان شماره ۱۲۴، واحد ۱ | تلفکس: ۸۷۷۵۴

www.abadgarangroup.com

info@abadgarangroup.com

The ABADGARAN INTERNATIONAL GROUP Technical Department is available to assist you in the correct use of our products and its resources are at your disposal entirely without obligation.

All data presented in this technical datasheet are based on our last researches in ABADGARAN CONSTRUCTION CHEMICALS laboratories and are just as a guide for choosing appropriate material. Therefore, users should conduct a sufficient investigation to establish the suitability and conformity of any product for intended uses.



موسسه استاندارد و تحقیقات صنعتی ایران
تأییدیه صلاحیت آزمایشگاه همکار



مرکز ملی تأیید صلاحیت ایران
ISO / IEC 17025



مجوز صادرات
به اتحادیه اروپا



استاندارد ملی ایران



واحد تولیدی نمونه ملی

تهران، خیابان سهروردی شمالی، خیابان شهید قندی غربی، ساختمان شماره ۱۲۴، واحد ۱ | تلفکس: ۸۷۷۵۴

www.abadgarangroup.com

info@abadgarangroup.com